## **ULTRALUBE #2 BLACK, RED**

## **Characteristics**

- $\bullet$  Very wide useful temperature range -50°F to 500 o F and 600 °F
- Excellent oxidation stability, no deposits.
- Prevent rust and corrosion.
- Good load carrying humidity.
- Protects against humidity.
- Saves maintenance dollars.

## **Application**

- Ball and roller bearing-can-slides-gear for appliance, au-motive, business machines, electric motor and instrument applications.
- Especially useful where thermal and oxidation stability are required.

## **Product Specification**

Typical Properties	101	102	103	104
Penetration	265-290	265-290	265-290	265-290
NLGI	2	2	2	2
Color	Red	Red	Red	Black
Dropping Point, o F	500	600	600	600
Thickener	Aluminum Complex	Aluminum Complex	Aluminum Complex	Aluminum Complex
Water Washout	2%	1%	1.5%	1.5%
Evaporation,210 o F	0.29%	0.29%	0.25%	0.25%
Oil Separation Rate	1.2%	1.2%	1.2%	1.2%
Rust & Corrosion Test	pass	pass	pass	pass
Timken OK Load Blean	75	75 Megalite	75 EP Additive	75 Moly-Graphite







ICS Integrate Chem and Service Co., Ltd.